

11721 East Cox Road, Kingman, AZ. 86401

(928) 757-5976

Roofing Felt





Warrior Roofing 15ASTM



Warrior Roofing 15W



Warrior Roofing 30ASTM



Warrior Roofing 30W



11721 East Cox Road Kingman, AZ. 86401

Email: bill@roseriverexportco.com

Phone: (928) 757-5976

Website: www.roseriverexportco.com





WARRIOR ROOFING MANUFACTURING SPECIFICATIONS

15 ASTM

Our #15 ASTM asphalt saturated organic felt is manufactured to meet or exceed the following:

ASTM - D226, Type 1 - Commonly called N. 15 Asphalt Felt

AND AS A PREPARED ROOFING ACCESSORY CLASSIFIRED BY U.L. LABORATORIES AS TO EXTERNAL FIRE EXPOSURE ONLY.

Dimensions and specifications of No. 15 ASTM asphalt felt are:

Width of roll: 36" + or - .7%

Area: 432 sq. ft.

Net mass of saturated felt: 11.5 lbs./00 sq. ft.

Net mass of saturant: 6.2 lbs./100 sq. ft.

Saturant Weight: Shall not be less than 1.2 times the weight of the moisture free felt.

Saturant efficiency: Shall be no less than 70% for type 15 asphalt saturated felt.

Packaging: The rolls are wrapped securely and the manufacturer's or distributor's

name, type, and specification markings are evident on the label.

UPC bar coding is included on all our labels.

<u>Important</u>: Warrior Roofing Manufacturing is a statewide approved vendor for the State of Florida. The Florida Product Approval Code # is FL 2346.



11721 East Cox Road Kingman, AZ. 86401

Email: bill@roseriverexportco.com

Phone: (928) 757-5976

Website: www.roseriverexportco.com





WARRIOR ROOFING MANUFACTURING

SPECIFICATIONS

15 W

Our #15W asphalt saturated organic felt is manufactured to meet or exceed the following:

ASTM - D4869, Type I

AND AS A PREPARED ROOFING ACCESSORY CLASSIFIRED BY U.L. LABORATORIES AS TO EXTERNAL FIRE EXPOSURE ONLY.

Dimensions and specifications of No. 15W asphalt felt are:

Width of roll: 36" + or - .7%

Area: 432 sq. ft.

Net mass of saturated felt: 8.0 lbs./100 sq. ft.

Net mass of saturant: 4.0 lbs./100 sq. ft.

Saturant Weight: Shall not be less than 1.0 times the weight of the moisture free felt.

Saturant efficiency: Shall be no less than 75% for type 15 asphalt saturated felt.

Packaging: The rolls are wrapped securely and the manufacturer's or distributor's

name, type, and specification markings are evident on the label.

UPC bar coding is included on all our labels.



11721 East Cox Road Kingman, AZ. 86401

Email: bill@roseriverexportco.com

Phone: (928) 757-5976

Website: www.roseriverexportco.com





WARRIOR ROOFING MANUFACTURING SPECIFICATIONS

#30 ASTM

Our #30 ASTM asphalt saturated organic felt is manufactured to meet or exceed the following:

ASTM - D226, Type II - Commonly called No. 30 Asphalt Felt

FED SPECIFICATION - HHR - 595B, TYPE 30

U.L. SPECIFICATION - U.L. STANDARD 55A FOR TYPE 30 ASPHALT SATURATED ORGANIC FELT

Dimensions and specifications of No. 30 ASTM asphalt felt are:

Width of roll: 36" + or - .7%

Area: 216 sq. ft.

Net mass of saturated felt: 26.0 lbs./100 sq. ft.

Net mass of saturant: 15.0 lbs./100 sq. ft.

Saturant Weight: Shall not be less than 1.5 times the weight of the moisture free felt.

Saturant efficiency: Shall be no less than 70% for type 30 asphalt saturated felt.

Packaging: The rolls are wrapped securely and the manufacturer's or distributor's

name, type, and specification markings are evident on the label.

UPC bar coding is included on all our labels.

<u>Important</u>: Warrior Roofing Manufacturing is a statewide approved vendor for the State of Florida. The Florida Product Approval Code # is FL 2346. Per Florida Building Code 1517.4.1 this product is marked with a yellow line signifying compliance with High Velocity Hurricane Zone requirements.



11721 East Cox Road Kingman, AZ. 86401

Email: bill@roseriverexportco.com

Phone: (928) 757-5976

Website: www.roseriverexportco.com





WARRIOR ROOFING MANUFACTURING SPECIFICATIONS

#30 W

Our #30W asphalt saturated organic felt is manufactured to meet or exceed ASTM-D4869, Type II

Width of roll: 36" + or - .7%

Area: 216 sq. ft.

Net mass of saturated felt: 8.0 lbs./100 sq. ft.

Net mass of saturant: 4.0 lbs./100 sq. ft.

Saturant Weight: Shall not be less than 1.0 times the weight of the moisture free felt.

Saturant efficiency: Shall be no less than 75% for type 30 asphalt saturated felt.

Packaging: The rolls are wrapped securely and the manufacturer's or distributor's

name, type, and specification markings are evident on the label.

UPC bar coding is included on all our labels.

<u>Important</u>: Warrior Roofing Manufacturing is a statewide approved vendor for the State of Florida. The Florida Product Approval Code # is FL 2346.